



Cold-Weather Caulking

Caulking during cold weather is one of the most difficult applications to do properly because of several adverse circumstances resulting from the low temperatures. PSI recommends the following:

- During application the temperature should be at least 40°F (4°C) and rising.
 - At temperatures near freezing and lower, water condensation and frost formation are possible and care must be taken to assure that all joints to be caulked are dry and frost-free.
 - Good workmanship in joint preparation is especially important. All joints must be clean, uniform in dimension and free of all traces of contamination by oil, dust, loose aggregate, rust, protrusions, rebar, sealers, coatings, release agents, waterproofing compounds, etc.
 - In the coldest weather, joints are at their maximum width due to contraction of building materials. Joints should be designed so that joint closure in hot weather will not exceed the compression limit of the sealant.
 - Sealant storage temperatures of 60 to 75°F (16 to 24°C) are suggested to facilitate mixing, handling and application.
- Cold temperatures slow the cure of most sealants. This should be considered in areas where physical damage may be inflicted on the partially-cured sealant.
 - Sealant that remains partially cured for extended periods may develop planes of weakness as a result of continuous joint movement.

Contact Details

Polymeric Systems, Inc., is a part of Whitford Worldwide.

For more information, please contact Polymeric Systems or Whitford Ltd. at:

Polymeric Systems, Inc.
47 Park Avenue

Elverson, PA, USA 19520

Tel: [1] (610) 286-2500

Email: sales@polymericsystems.com

Website: polymericsystems.com



Whitford Ltd.

11 Stuart Road, Manor Park
Runcorn, Cheshire, UK WA7 1TH

Tel: [44] (0) 1928 571000

Email: salesuk@whitfordww.com

Website: whitfordww.com

Toll Free: 800-CAULK IT (800-228-5548)

NON-WARRANTY: ALL RECOMMENDATIONS, STATEMENTS AND TECHNICAL DATA CONTAINED HEREIN ARE BASED ON TESTS WE BELIEVE TO BE RELIABLE AND CORRECT, BUT ACCURACY AND COMPLETENESS OF SAID TESTS ARE NOT GUARANTEED AND ARE NOT TO BE CONSTRUED AS A WARRANTY, EITHER EXPRESS OR IMPLIED. USER SHALL RELY ON HIS OWN INFORMATION AND TESTS TO DETERMINE SUITABILITY OF THE PRODUCT FOR THE INTENDED USE, AND USER ASSUMES ALL RISK AND LIABILITY RESULTING FROM THIS USE OF THE PRODUCT. MANUFACTURER'S SOLE RESPONSIBILITY SHALL BE TO REPLACE THAT PORTION OF THE PRODUCT OF THE MANUFACTURER THAT PROVES TO BE DEFECTIVE. MANUFACTURER SHALL NOT BE LIABLE TO THE BUYER OR ANY THIRD PARTY FOR INJURY, LOSS OR DAMAGE DIRECTLY OR INDIRECTLY RESULTING FROM USE OF, OR INABILITY TO USE, THE PRODUCT. RECOMMENDATIONS OR STATEMENTS OTHER THAN THOSE CONTAINED IN A WRITTEN AGREEMENT SIGNED BY AN OFFICER OF THE MANUFACTURER SHALL NOT BE BINDING UPON THE MANUFACTURER.

3004-0213