



MIX2FIX[®] FC Translucent Adhesive

(formerly PSI-326 Fast-Cure Epoxy Repair Compound)

Product description

MIX2FIX FC Translucent Adhesive is a low-odor, two-component, modified epoxy adhesive that cures rapidly at room temperature with exceptional tensile adhesion and peel strength to a wide variety of substrates. Just a few minutes after application it forms a tough bond without the need for clamping.

Basic uses

MIX2FIX FC Translucent Adhesive may be used as a general-purpose adhesive to bond wood, metal, fiberglass, glass, ceramics and many hard plastics. It forms a strong bond that is tough enough to be filed, drilled, tapped, or sanded after final cure.

Benefits

- Contains no volatile solvents and does not shrink upon curing.
- High peel strength and impact resistance for both industrial and household repairs.
- Excellent adhesion to a wide variety of substrates.
- Fast-curing.
- Thixotropic.

Application limitations

- Does not adhere to PTFE, polyethylene or polypropylene.
- Becomes very hot during cure; do not mix more than 8 oz. (224 g.) total at one time, i.e. 4 oz. (112 g.) each of Part A and Part B.
- See performance data for temperature limits.
- Do not apply at temperatures below 41°F (5°C).
- Not intended for structural applications.

Color

Cured color is Translucent.

Packaging

Available in 2-lb. (907g) kits. Special packaging available upon request.

How to use

Surface preparation: To achieve optimum adhesion, surfaces should be dry and free of grease or dirt. Scuffing or sanding the surface prior to cleaning helps insure a good bond.

Mixing and application: Wear impermeable gloves when mixing or handling uncured product. Mix equal portions of resin (Part A) and hardener (Part B) by weight or volume until uniform. Do not mix more than 8 oz. (224 g.) total at one time, i.e., 4 oz. (112 g.) each of Part A and Part B. Material may become hot during cure. Use within 3 minutes of mixing. Remove excess material before product begins to set.

Allow MIX2FIX FC Translucent Adhesive to harden until a strong bond has formed before handling or returning to service, normally 60 to 90 minutes depending on the nature of the application. Product cures faster at higher temperatures and larger volumes. Product cures slower at lower temperatures and in thin sections.

Shelf life: One year from date of shipment when stored in original, unopened containers at 75°F (24°C).

Health precautions

- Contains Epoxy Resin. Epoxies are skin/eye irritants and known sensitizers. Direct product contact may cause an allergic reaction in some individuals. Avoid skin/eye contact. Wear impermeable gloves when mixing or handling uncured product.
- Inhalation of dust may be harmful. Avoid inhalation of dust. Wear dust mask and protective eyewear when sanding cured product.
- Ingestion of product may be harmful. Avoid ingestion.
- KEEP OUT OF THE REACH OF CHILDREN.

For additional health and safety information, consult a Safety Data Sheet.

Performance Data*		
Properties	Results	Test Methods
Uncured Properties		
Composition	Two-part epoxy adhesive	
Physical appearance	Gel	
Odor (hardener)	Strong sulphurous smell (no odor when cured)	
Mixing ration by weight or volume	1:1	
Mixed density	9.76 lb/gl (1.17 g/cm ³)	
Application temperature	50 to 95°F (10 to 35°C)	
Work life, 3 grams at 75°F (24°C)	5 minutes	
Handling time at 75°F (24°C)	1 hour	ASTM D1002
Return to service time at 75°F (24°C)	16 hours	
Cured Mechanical Properties		
Physical appearance when cured	Translucent solid	
Hardness, Shore D	65	ASTM D2240
Tensile strength	5,000 psi (34 MPa)	ASTM D925
Lapshear tensile adhesive strength		ASTM D1002
Steel to steel	1,000 psi (7.0 MPa)	
Aluminum to aluminum	1,100 psi (7.6 MPa)	
Glass to glass	>100 psi (0.7 MPa)	
Compressive strength	9,000 psi (62 MPa)	ASTM D695
Temperature limits		
Continuous	-40°F to +200°F (-40°C to +93°C)	
Intermittent	-40°F to +250°F (-40°C to +121°C)	
Chemical resistance	Resistant to hydrocarbons, ketones, alcohols, esters, halocarbons, aqueous salt solutions, dilute acids and bases	
* Typical properties are for information only, not for purposes of specification. The data above represents product performance in ideal laboratory conditions. Individual users' experience may vary depending on application conditions.		

Contact Details

Polymeric Systems, Inc., is a part of Whitford Worldwide.
For more information, please contact Polymeric Systems or Whitford Ltd. at:

Polymeric Systems, Inc.
47 Park Avenue
Elverson, PA, USA 19520
Tel: [1] (610) 286-2500
Email: sales@polymericsystems.com
Website: polymericsystems.com



Whitford Ltd.
11 Stuart Road, Manor Park
Runcorn, Cheshire, UK WA7 1TH
Tel: [44] (0) 1928 571000
Email: salesuk@whitfordww.com
Website: whitfordww.com

Toll Free: 800-CAULK IT (800-228-5548)

NON-WARRANTY: ALL RECOMMENDATIONS, STATEMENTS AND TECHNICAL DATA CONTAINED HEREIN ARE BASED ON TESTS WE BELIEVE TO BE RELIABLE AND CORRECT, BUT ACCURACY AND COMPLETENESS OF SAID TESTS ARE NOT GUARANTEED AND ARE NOT TO BE CONSTRUED AS A WARRANTY, EITHER EXPRESS OR IMPLIED. USER SHALL RELY ON HIS OWN INFORMATION AND TESTS TO DETERMINE SUITABILITY OF THE PRODUCT FOR THE INTENDED USE, AND USER ASSUMES ALL RISK AND LIABILITY RESULTING FROM THIS USE OF THE PRODUCT. MANUFACTURER'S SOLE RESPONSIBILITY SHALL BE TO REPLACE THAT PORTION OF THE PRODUCT OF THE MANUFACTURER THAT PROVES TO BE DEFECTIVE. MANUFACTURER SHALL NOT BE LIABLE TO THE BUYER OR ANY THIRD PARTY FOR INJURY, LOSS OR DAMAGE DIRECTLY OR INDIRECTLY RESULTING FROM USE OF, OR INABILITY TO USE, THE PRODUCT. RECOMMENDATIONS OR STATEMENTS OTHER THAN THOSE CONTAINED IN A WRITTEN AGREEMENT SIGNED BY AN OFFICER OF THE MANUFACTURER SHALL NOT BE BINDING UPON THE MANUFACTURER.

2008-0913