



QuikTitanium®

Product description

QuikTitanium is a hand-mixable, titanium-reinforced epoxy putty stick specifically formulated to bond and repair materials that will be exposed to high temperatures in industrial maintenance applications. Each stick contains pre-measured portions of base and activator throughout. No measuring or mixing tools are needed - just cut, mix and apply.

When mixed to a uniform color, the materials combine to form a polymer compound that can be molded into shapes or used to build up, repair and patch almost anything. This industrial-strength product cures tough and hard and bonds tenaciously to metals. After 8 hours of cure, QuikTitanium can be machined, tapped, drilled, ground or filed.

Basic uses

QuikTitanium can be used to repair tanks, iron pipes, equipment, tools, stripped threads, blow holes, patterns, castings, molds and ductwork.

Benefits

- Solventless.
- Low odor.
- Long pot life.
- Service temperature -40 to +500°F (-40 to +260°C).

Application limitations

- Does not adhere to polyethylene, polypropylene or PTFE.
- Not intended for use in structural applications.

Color

Golden-brown Titanium color.

Packaging

Packaged in a reusable clear plastic tube with a plastic friction top, 12 or 24 tubes per display carton, two display cartons in a master carton.

How to use

Surface preparation: To achieve optimum adhesion, surfaces must be clean and free of oil, grease, corrosion and dirt. Scuffing or sanding the surface prior to cleaning helps ensure a

good bond.

Mixing and application: Wear impervious gloves when mixing or handling uncured product. Twist or cut off required amount with gloved fingers, then mix by kneading to a uniform color. If mixing is difficult, warm QuikTitanium to room temperature or slightly above. Apply to the repair surface within 1 hour of mixing. Force into any cracks or holes to be filled and strike off excess material before hardening begins, preferably with a tool moistened with clean water. Heating QuikTitanium or applying to warm surfaces will accelerate the cure. For a smooth cured appearance, rub with water or a damp cloth prior to hardening.

After 2 hours the epoxy will form a tenacious bond. Curing at higher temperatures (150°F/65°C) will provide a stronger bond and faster hardening; lower temperatures will retard the cure. After 8 hours at room temperature QuikTitanium can be drilled, tapped, and sanded.

Shelf life: One year minimum from date of shipment when stored in original, unopened container in a dry area at temperatures below 75°F (24°C).

Health precautions

- Contains Epoxy Resin, Tri (dimethylaminomethyl) phenol, and Aliphatic Amines. Epoxies are skin/eye irritants and known sensitizers. Direct product contact may cause an allergic reaction in some individuals. Avoid skin/eye contact. Wear impermeable gloves when mixing or handling uncured product.
- Inhalation of dust may be harmful. Avoid inhalation of dust. Wear dust mask and protective eyewear when sanding cured product.
- Ingestion of product may be harmful. Avoid ingestion.
- KEEP OUT OF REACH OF CHILDREN.

For additional health and safety information, consult a Safety Data Sheet.

Performance data appears on reverse side.

Performance Data*		
Properties	Results	Test Methods
Uncured Properties		
Work life at 75°F (24°C)	1.5 to 2 hours	
Non-volatile content	>99%	
Density	16.5 lb/gal (1.90 g/cm ³)	
Functional cure (lap shear tensile strength=200 psi)	8 hours	
Cure time to full cure at 70°F (21°C)	3 days	
Cured Mechanical Properties		
Shore D hardness		
at 75°F (24°C)	80	ASTM D2240
at 500°F (260°C)	48	
Lap shear tensile strength (steel to steel)		
Cured at 75°F (24°C) for 24 hrs	250 lbs (2 MPa)	ASTM D1002
Cured at 150°F (65°C) for 24 hrs	750 lbs (5 MPa)	
High-temperature lap shear strength (steel to steel)		
Cured at 75°F (24°C) for 24 hrs + 500°F (260°C) for 1 hr.	250 lbs (2 MPa)	ASTM D1002
Compressive strength	8,000 psi (55 MPa)	ASTM D695
Shrinkage	<1%	ASTM D2566
High-temperature weight loss (24 hours)	<1% at 400°F (204°C) <2% at 500°F (260°C)	
Tg by DSC	134°F (57°C)	
Temperature limits		
Continuous	-40 to +450°F (-40 to +232°C)	
Intermittent	-40 to +500°F (-40 to +260°C)	
Chemical resistance	Resistant to hydrocarbons, ketones, esters, alcohols, halocarbons, aqueous salt solutions, and dilute acids and bases	
Cured Electrical Properties		
Electrical resistance	30,000 megohms-cm	ASTM D257
Dielectric strength	300 volts/mil	ASTM D149
<i>Typical properties are for information only, not for purposes of specification. The data above represents product performance in ideal laboratory conditions. Individual users' experience may vary depending on application conditions.</i>		

Contact Details

Polymeric Systems, Inc., is a part of Whitford Worldwide.

For more information, please contact Polymeric Systems or Whitford Ltd. at:

Polymeric Systems, Inc.

47 Park Avenue

Elverson, PA, USA 19520

Tel: [1] (610) 286-2500

Email: sales@polymericsystems.com

Website: polymericsystems.com



Whitford Ltd.

11 Stuart Road, Manor Park
Runcorn, Cheshire, UK WA7 1TH

Tel: [44] (0) 1928 571000

Email: salesuk@whitfordww.com

Website: whitfordww.com

Toll Free: 888-EPOXY FIX (888-376-9934)

NON-WARRANTY: ALL RECOMMENDATIONS, STATEMENTS AND TECHNICAL DATA CONTAINED HEREIN ARE BASED ON TESTS WE BELIEVE TO BE RELIABLE AND CORRECT, BUT ACCURACY AND COMPLETENESS OF SAID TESTS ARE NOT GUARANTEED AND ARE NOT TO BE CONSTRUED AS A WARRANTY, EITHER EXPRESS OR IMPLIED. USER SHALL RELY ON HIS OWN INFORMATION AND TESTS TO DETERMINE SUITABILITY OF THE PRODUCT FOR THE INTENDED USE, AND USER ASSUMES ALL RISK AND LIABILITY RESULTING FROM THIS USE OF THE PRODUCT. MANUFACTURER'S SOLE RESPONSIBILITY SHALL BE TO REPLACE THAT PORTION OF THE PRODUCT OF THE MANUFACTURER THAT PROVES TO BE DEFECTIVE. MANUFACTURER SHALL NOT BE LIABLE TO THE BUYER OR ANY THIRD PARTY FOR INJURY, LOSS OR DAMAGE DIRECTLY OR INDIRECTLY RESULTING FROM USE OF, OR INABILITY TO USE, THE PRODUCT. RECOMMENDATIONS OR STATEMENTS OTHER THAN THOSE CONTAINED IN A WRITTEN AGREEMENT SIGNED BY AN OFFICER OF THE MANUFACTURER SHALL NOT BE BINDING UPON THE MANUFACTURER.

4012-0213